

JP37x Series Epoxy Primers

Background

JP37x Series Epoxy Primers are two-component, non-chrome coatings designed to provide superior corrosion protection and adhesion when applied over properly cleaned and sanded bare metal, fiberglass and painted surfaces. JP37x Series Epoxies are available in gray, white or black.

JP37x Series Epoxy Primer

Primer

JP371 Epoxy Primer-White
JP375 Epoxy Primer-Gray
JP377 Epoxy Primer-Black

Catalyst

JH3770 Epoxy Primer Hardener

Thinner

Acetone (optional)

Compatible Surfaces

Cleaned, sanded, bare or primed steel, galvanized and aluminum. Sanded and cleaned body filler, cured, cleaned and sanded OEM and refinish coatings

JP37x Series Epoxy Primers may be applied over:

JP202 2K Primer Surfacer
JP209 Gray Polyester Primer/ Filler
JP233 1K Acrylic Primer
JP285 2K Urethane Surfacer
JP301 Plastic Adhesion Promoter

JP37x Series Epoxy Primers may be overcoated with:

JP202 2K Primer Surfacer
JP209 Gray Polyester Primer/Filler
JP233 1K Acrylic Primer
JP285 2K Urethane Surfacer
JP33x 2K Urethane Sealer
JB Acrylic Basecoat
JBP Acrylic Urethane Basecoat
JE Acrylic Enamel
JE Acrylic Enamel / Activated
JAU Direct Gloss Acrylic Urethane

Preparation

Surface cleaning


JX101 Wax and Grease Remover, JX992 Plastic Cleaner, SXA330 Wax and Grease Remover, SWX350 H₂O-So-Clean.

Sanding

120 - 180 grit on bare metal
220 - 320 grit on old finishes, body filler

Mixing

Ratios

	JP37x	JH3770	*Acetone
	2	1	up to 1/2 part

*Optional

Note: Allow a 15 minute induction period before applying.

Potlife 8 hours at 70°F (21°C)

Additives None

Application

Coats



1 or 2 coats

Air pressure



HVLP	8 - 10 psi at the air cap
Conventional	45 - 50 psi at the gun

Gun setup

1.3 - 1.6 mm or equivalent

Dry Times

Air dry



1 coat 15 minutes at 70°F (21°C)

2 coats 30 minutes at 70°F (21°C)

Tape Time: Minimum 6 Hours

JP37X Series Epoxy Primers **must** be scuffed and reapplied if allowed to stand more than 3 days.

Clean Up

Clean spray guns, gun cups, storage pots thoroughly with JR Reducer, JT501 General Purpose Solvents or other appropriate clean up solvent after each use.

Follow EPA guidelines for proper storage and disposal of solvent-borne waste paint.

Properties

VOC

Applied	JP371	4.53 lbs./gal (551gm/L)
Less Exempts (2:1)	JP375	4.54 lbs./gal (539gm/L)
	JP377	4.54 lbs./gal (539gm/L)

Applied (2:1) + up to 1/2 part acetone
4.53 - 4.54 lbs./gal (543 - 544gm/L)

Dry Film build per coat

Applied (2:1) 1.0 mil

Square foot coverage at 1 mil

Applied (2:1) 577 sq. ft. / gal. @ 100% transfer

Limitations

SHOP-LINE[®] products should not be combined with components of other product lines.

Precautionary Information:

The contents of this package may have to be blended with other components before the product can be used. Before opening the packages, be sure you understand the warning messages on the labels of all components, since the mixture will have the hazards of all its parts. Spray equipment must be handled with due care and in accordance with manufacturer's recommendations. Follow label directions for respirator use. Wear eye and skin protection. Observe all applicable precautions.

Medical Response:

EMERGENCY MEDICAL OR SPILL CONTROL INFORMATION (412) 434-4515; IN CANADA (514) 645-1320.

Material Safety Data Sheet:

Material Data Safety Sheets for the PPG products mentioned in this publication are available through your PPG Shop-Line Distributor.

Shop-Line and *H₂O-So-Clean* are trademarks of PPG Industries Ohio, Inc.

